



MORTELAN

SOLUCIONES PARA TU CASA

MORTELAN Cemento cola multiusos

- Fixing of tiles, porcelain, mosaics and stone material.
- Interior and exterior pavements and coatings.
- Special swimming pools, facades and radiant air conditioning.

Description and uses of the product

Deformable, no vertical slip, cement adhesive and high working time, allowing in this way the rectification of pieces.

Its excellent features make this adhesive ideal for the installation of all types of ceramic tiles (with or without absorption), marble, granite and natural or reconstituted stone, including ceramic pieces with very low thickness (up to 3mm)

It is extensively used in interiors, exteriors and facade coverings on cement mortar, concrete surfaces, etc. It is also suitable for the installation of heavy-traffic flooring (shopping centres, airports, etc.) and floors with under-floor heating, all types of plasterboard laminate surfaces, and even for overlaying ceramic pieces on antique tiled floors, without the need for the previous application of a coat of bonding primer.

It can be applied up to a thickness of 15mm, thereby providing a solution for possible flatness problems on the surface and, also guaranteeing that there is no vertical slip in the ceramic tiles to be installed.

How to use

- 1) Prepare and clean substrate.
- 2) Water to add 0.600 litres / bag 2 kg.
- 3) Setting time 4-6 hours.
- 4) Mixture workable for 30 minutes.
- 5) Clean tools with water.

Recommendations:

Application temperature +5°C to +30°C.

Mix until you get a thick paste.

Apply on the support and / or whole surface of the tile with a toothed trowel.

Fit the tile and press it firmly into place, leaving a joint of 3 to 5 mm.

Clean the tools and tiles with water immediately after use.

Do not use on gypsum or metal supports or those with a humidity more than 3 %.

Features

Colour: White.

High performance ceramic mortar, type C2TE S1. Immersion resistant.

Used in a thin layer.

Excellent bonding and flexibility qualities.

Setting time: 4 – 6 h.

Correction time: 30 min.

Theoretical consumption 2,5 – 3 kg/m².

Bonding strength: > 10 kg/cm².

Shelf life 12 months if sheltered.

MORTELAN Cemento cola multiusos 20/03/2015

MORTELAN Cemento cola multiusos

Yield

Single spread: +/- 2.5 kg /m²

Double spread: +/- 5.5 kg /m²

Presentation and delivery

2 kg inner polypropylene bag in plastic bucket and pallet with 160 buckets (320 kg).

6 kg (3 x 2 kg) inner polypropylene bag in plastic bucket and pallet with 105 buckets (630 kg).

Precautionary statements



Danger

Hazard statements

H315: Causes skin irritation

H318: Causes serious eye damage

H317: May cause an allergic skin reaction

H335: May cause respiratory irritation

Precautionary statements

P261: Avoid breathing dust/fume/ gas/mist/vapours/spray.

P280: Wear protective gloves/protective clothing/eye protection/face protection.

P302 + P352 – IN CASE OF SKIN CONTACT: Wash with plenty of soap and water.

P305 + P351 + P338 – IN CASE OF EYES CONTACT: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P310: Immediately call a POISON CENTER/doctor

1999/45/CE The product contains a chromium VI reducing agent; the period of declared efficiency is that indicated on the packaging.