

PLASTE EXTERIORES

FIBER
REINFORCED

Repairs, remakes, cover cracks and joints.

Waterproofing pools, ponds, flower pots, etc.

Salt and sulphated water resistant



Description and uses of the product

Fibre-reinforced powder mortar, flexible, high adhesion and low shrinkage, designed for plastering, waterproofing, smoothing and cover cracks in interior and exterior coatings and ceilings.

It provides a fine, durable and high quality finish, and can be applied on substrates of cement, concrete, stone and others of similar nature.

'Fine finish'

Suitable for the renovation and protection of concrete, blocking efflorescence and making small anchors, as well as for waterproofing balconies, pillars, cornices, overhangs, together brick, chipped in swimming pools and other repairs in wet environments.

Resistant to seawater, aggressive water (pH>5) and pressure and counterpressure water.

Let's be coated with paints, without prior primer.

How to use

1. Prepare and clean substrate.
2. Water to add 0,350 litres / sac 1,5 kg.
3. Mixture workable for 30 minutes.
4. Performance 1,2 / 1,5 kg /m²
5. Clean tools with water.

Recommendations

Do not use at low temperatures.

Stir firmly until a soft and even paste obtained.

Do not stir again, once it begins to set.

Remove loose materials and dirt from the surface and dampen very absorbent backgrounds to prevent shrinkage and to improve bonding.

Apply with a trowel or spatula making sure the paste penetrates to the bottom and by widening cracks if necessary.

Do not use on gypsum or metal surfaces.

Features

Colour grey.

Resistance to compression: > 20 N/mm²

Thickness obtainable: between 1 and 15 mm.

Drying time: 48 hours/mm.

Shelf life 12 months if sheltered.

Yield

It varies depending on the type of application.

Theoretical consumption: 1,5 kg/m² per mm thickness.

Presentation and delivery

1,5 kg bucket: 1.5 kg polypropylene bag in a plastic mixing bucket.

4,5 kg bucket: 3 polypropylene bags of 1.5 kg (3 x 1.5 kg) in a plastic mixing bucket.

Safety data



GHS07

Hazard statements

- H315** Causes skin irritation.
H318 Causes serious eye damage.
H317 May cause an allergic skin reaction.
H335 May cause respiratory irritation.

Precautionary statements

- P261** Avoid breathing dust/fume/ gas/mist/vapours/spray.
P280 Wear protective gloves/protective clothing

/eye protection /face protection.

P302 + P352 IN CASE OF SKIN CONTACT:
Wash with plenty of soap and water.

P305 + P351 + P338 IN CASE OF EYES CONTACT:
Rinse cautiously with water for several minutes.
Remove contact lenses, if present and easy to do.
Continue rinsing.

P310 Immediately call a POISON CENTER/doctor
1999/45/CE The product contains a chromium VI reducing agent; the period of declared efficiency is that indicated on the packaging.